

Abstract of the Disclosure

Crosslinker compositions consisting essentially of 50 to 95 weight percent monomeric C₁ to C₈ alkoxymethyl melamine derivatives containing not more than about 0.20 wt. % of imino (>N-H) groups. Such compositions further comprise 5 to 50 weight percent oligomeric C₁ to C₈ alkoxymethyl melamine derivatives and are useful for low temperature curing of functional resins, e.g. with active hydroxyl groups, for wood, automotive, appliance, coil and other coatings.